



Datum	artikelnummer
6/12/2021	506202

Cuore SPT 5000 Color

Composition	Cuore SPT 5000 Color is a solvent free, light fast, colour paste.
Application	Cuore SPT 5000 Color is applied as an addition to one of the transparent coatings from the Cuore SPT 5000 Color range.
Technical properties	Density Resin + Hardener 1800 kg/m ³
Mixing ratio	62,5 Parts by weight transparent coating 7030** 37,5 Parts by weight Colour Paste 706000
Mixing procedure	1) Open the container with the resin and mix the material till it is homogenous. 2) Open the container with the hardener and add the hardener to the resin. 3) Mix both components mechanically about 2 minutes till a homogenous mixture is formed. A well- mixed material is uniform in color without containing clear or dark spots. 4) To avoid mixing errors or unmixed residue; pour the mixed material into a clean and empty container and mix again for a short time. Never use unmixed residue of the material.
Colour - structure - gloss	On request from RAL/NCS - smooth – mat
Packaging	1,5 kg packaging
Precautions	It is important that applicable requirements for working with synthetics are adhered to. It is therefore advised to avoid skin and eye contact, by using creams and/or liquid-proof gloves, safety glasses, etc. When processing Cuore SPT 5000 Color especially in small, enclosed spaces, it is recommended to ventilate very well.
Shelf life	In the original, unopened packaging, stored in a dry place between 5 °C and 25 °C, Cuore SPT 5000 color has a shelf life of 4 months maximum. Note: Cuore SPT 5000 color may not be stored or exposed to temperatures beneath 5 °C.
Attention	Cuore SPT 5000 Color may only be applied by trained and professional installers.

Onze adviezen met betrekking tot de technische toepassing in woord, geschrift of door middel van proeven, worden naar beste weten verstrekt, doch gelden slechts als vrijblijvende aanwijzingen, ook ten aanzien van eventueel beschermende rechten van derden. Zij ontslaan u niet van de verplichting, de door ons geleverde producten op hun geschiktheid voor de beoogde procedures en doeleinden te controleren. Toepassing, gebruik en verwerking van de producten vinden plaats buiten onze controlemogelijkheden. Zij vallen derhalve onder uw eigen verantwoordelijkheid. In geval van eigen aansprakelijkheid blijft deze, voor alle schadegevallen, beperkt tot de waarde van de door ons geleverde en door u gebruikte goederen. Vanzelfsprekend garanderen wij u de goede kwaliteit van onze producten, e.e.a. volgens de in onze algemene verkoop- en leveringsvoorwaarden genoemde maatstaven.